




COMMERCIAL - TECHNICAL DATA / Tecnologia

FLEX

74% POLYESTER
26% ELASTANE

Test Method for Knit Fabrics		STANDARD (estandar)		DIGITAL PRINT		
Width / Ancho NTC 228-2011		In	Cms	In	Cms	
		Phisic / Físico	57	145	57	145
		Useful / Util	56	142	55	140
Weight / Peso ASTM D 3776-2009		Oz/syd	Gsm	Oz/syd	Gsm	
		7.4	250	7.5	254	
Shrinkage / Cambio dimensional (%) AATCC 135-2004 / IN504-15	Lenght / Longitud	5%		5%		
	Trans / Transversal	4%		4%		
Spirality after laundry / Viraje despues del lavado (%) ISO16322-2-2005	Lenght / Longitud	3%		3%		
	Trans / Transversal	3%		3%		
Color fastness to wash / Solidez al lavado (gray scale) AATCC 61-2007	Change / Cambio	4		4		
	Stain / Transf	3		3		
Dye transfer to storage. Option II (gray scale) / Transferencia del color por almacenamiento. Opcion II AATCC 163-2007	Stain / Transf	4		4		
Color fastness to light (gray scale) / Solidez a la luz BS 1006-1990	Change / Cambio	4		4		
Color fastness to crocking (gray scale) / Solidez al frote AATCC 8-2007	Dry / Seco	4		4		
	Wet / Húmedo	3		3		
Color Fastness to perspiration (gray scale) / Solidez a la transpiración AATCC 15-2007	Change / Cambio	4		4		
	Stain / Transf	3		3		
Pilling / Pilling (Photographic) NTC 2051-2 / 2003		3		3		
Type of fabric / Tipo de tejido				Knit		
Tariff code white: 6004100000				Reviewed by		
Recommendations: Rest for 20 to 24 hours before cutting. Recommend testing before any tratment or application other than cutting and sewing.				 ANDRES LOPEZ		
