



COMMERCIAL - TECHNICAL DATA / Tecnologia



**NEW YORK ECO**  
95% RECYCLED POLY  
5%SPANDEX

Test Method for Knit Fabrics		STANDARD (estandar)		DIGITAL PRINT	
		In	Cms	In	Cms
Width / Ancho NTC 228-2011	Phisic / Fisico	63	160	63	160
	Useful / Util	62	157	61	155
Weight /Peso ASTM D 3776-2009		<b>Oz/syd</b>	<b>Gsm</b>	<b>Oz/syd</b>	<b>Gsm</b>
		9.1	308	9.2	312
Shrinkage / Cambio dimensional (%) AATCC 135-2004 / IN504-15	Lenght / Longitud	5%		5%	
	Trans / Transversal	4%		4%	
Spirality after laundry / Viraje despues del lavado (%) ISO16322-2-2005	Lenght / Longitud	3%		3%	
	Trans / Transversal				
Color fastness to wash / Solidez al lavado (gray scale) AATCC 61-2007	Change / Cambio	4		4	
	Stain / Transf	3		3	
Dye transfer to storage. Option II (gray scale) / Transferencia del color por almacenamiento. Opcion II AATCC 163-2007	Stain / Transf	4		4	
Color fastness to light (gray scale) / Solidez a la luz BS 1006-1990	Change / Cambio	4		4	
Color fastness to crocking (gray scale) / Solidez al frote AATCC 8-2007	Dry / Seco	4		4	
	Wet / Húmedo	3		3	
Color Fastness to perspiration (gray scale) / Solidez a la transpiración AATCC 15-2007	Change / Cambio	4		4	
	Stain / Transf	3		3	
Pilling / Pilling (Photographic) NTC 2051-2 / 2003		3		3	
Type of fabric / Tipo de tejido				Knit	
				<b>Reviewed by</b>	
<b>Recommendations:</b> Rest for 20 to 24 hours before cutting. Recommend testing before any tratment or application other than cutting and sewing.				 <b>ANDRES LOPEZ</b>	