


COMMERCIAL - TECHNICAL DATA / Tecnologia

BERLIN ECO

100% VISCOSE ECOVERO

Test Method for Woven Fabrics		STANDARD (estandar)		DIGITAL PRINT	
Width / Ancho NTC 228-2011		In	Cms	In	Cms
	Phisic / Físico	51	130	51	130
	Useful / Util	50	127	50	127
Weight / Peso ASTM D 3776-2009		Oz/syd	Gsm	Oz/syd	Gsm
		3.8	130	3.9	131
Shrinkage / Cambio dimensional (%) 135-2004 / IN504-15	Lenght / Longitud	6%		6%	
	Trans / Transversal	5%		5%	
Spirality after laundry / Viraje despues del lavado (%) ISO16322-2-2005	Lenght / Longitud	3%		3%	
	Trans / Transversal				
Color fastness to wash / Solidez al lavado (gray scale) AATCC 61-2007	Change / Cambio	4		4	
	Stain / Transf	3		3	
Dye transfer to storage. Option II (gray scale) / Transferencia del color por almacenamiento. Opcion II AATCC 163-2007	Stain / Transf	4		4	
Color fastness to light (gray scale) / Solidez a la luz BS 1006-1990	Change / Cambio	4		4	
Color fastness to crocking (gray scale) / Solidez al frote AATCC 8-2007	Dry / Seco	4		4	
	Wet / Húmedo	3		3	
Color Fastness to perspiration (gray scale) / Solidez a la transpiración AATCC 15-2007	Change / Cambio	4		4	
	Stain / Transf	3		3	
Pilling / Pilling (Photographic) NTC 2051-2 / 2003		3		3	
Type of fabric / Tipo de tejido				Woven	
				Reviewed by	
Recommendations: Rest for 20 to 24 hours before cutting. Make prior tests of fusion or dyeing if is required. High shrinkage fabric.				 ANDRES LOPEZ	
