



COMMERCIAL - TECHNICAL DATA / Tecnologia

FABRIC NAME

BIKRAM ECO

YARN/CONSTRUCTION:	50D+40D 32 NEEDLE	COMP:	85% RECYCLED POLYESTER 15%SPANDEX	
		H.S CODE	60053700	
Test Method for Knit Fabrics			STANDARD (PFD/PFDPP)	
Width / Ancho NTC 228-2011	Phisic / Fisico	In	Cms	
		61	155	
Weight /Peso ASTM D 3776-2009	Useful / Util	59	150	
		Oz/syd	Gsm	
Shrinkage / Cambio dimensional (%) AATCC 135-2004 / IN504-15	Lenght / Longitud	6.8	230	
		8%	8%	
Spirality after laundry / Viraje despues del lavado (%) ISO16322-2-2005	Trans / Transversal	5%		
		3.0-4.0		
Color fastness to wash / Solidez al lavado (gray scale) AATCC 61-2007	Change / Cambio	3.0-4.0		
		Stain / Transf	3.0-4.0	
Dye transfer to storage. Option II (gray scale) / Transferencia del color por almacenamiento. Opcion II AATCC 163-2007	Stain / Transf		3.0-4.0	
		Color fastness to light (gray scale) / Solidez a la luz BS 1006-1990	Change / Cambio	3
Color fastness to crocking (gray scale) / Solidez al frote AATCC 8-2007	Dry / Seco			3.0-4.0
		Color Fastness to perspiration (gray scale) / Solidez a la transpiración AATCC 15-2007	Wet / Húmedo	3
Pilling / Pilling (Photographic) NTC 2051-2 / 2003	Change / Cambio			3.0-4.0
		Type of fabric / Tipo de tejido	Stain / Transf	3.0-4.0
				3
		Knit		

Recommendations:

