



COMMERCIAL - TECHNICAL DATA / Tecnologia

FABRIC NAME

DRILL MAGNUM

YARN/CONSTRUCTION:	10S(C)*10S(C) /72*40	COMP:	100% COTTON
		H.S CODE	5209220000
Test Method for Woven Fabrics			STANDARD (WHITE 00/PFD)
Width / Ancho NTC 228-2011	Phisic / Fisico	In 67	Cms 170
	Useful / Util	66	167
Weight /Peso ASTM D 3776-2009		Oz/syd 7.7	Gsm 260
	Shrinkage / Cambio dimensional (%) AATCC 135-2004 / IN504-15	Lenght / Longitud Trans / Transversal	4% 4%
Spirality after laundry / Viraje despues del lavado (%) ISO16322-2-2005	Lenght / Longitud	2%	
	Trans / Transversal		
Color fastness to wash / Solidez al lavado (gray scale) AATCC 61-2007	Change / Cambio	4	
	Stain / Transf	4	
Dye transfer to storage. Option II (gray scale) / Transferencia del color por almacenamiento. Opcion II AATCC 163-2007	Stain / Transf	4	
Color fastness to light (gray scale) / Solidez a la luz BS 1006-1990	Change / Cambio	3	
Color fastness to crocking (gray scale) / Solidez al frote AATCC 8-2007	Dry / Seco	4	
	Wet / Húmedo	3	
Color Fastness to perspiration (gray scale) / Solidez a la transpiración AATCC 15-2007	Change / Cambio	4	
	Stain / Transf	4	
Pilling / Pilling (Photographic) NTC 2051-2 / 2003			3
Type of fabric / Tipo de tejido			Woven

Recommendations:

