



**COMMERCIAL - TECHNICAL DATA / Tecnologia**

**FABRIC NAME**

**WAFFLE**

<b>YARN/CONSTRUCTION:</b>	<b>JC 32S+70DSP</b>	<b>COMP:</b>	<b>COTTON/SPANDEX 96/4</b>
		<b>H.S CODE</b>	<b>6006210000</b>
<b>Test Method for Knit Fabrics</b>			<b>STANDARD ( PFD/PFDPP)</b>
Width / Ancho NTC 228-2011	Phisic / Fisico	<b>In</b> 57	<b>Cms</b> 145
	Useful / Util	55	140
Weight /Peso ASTM D 3776-2009		<b>Oz/syd</b> 6.2	<b>Gsm</b> 210
	Shrinkage / Cambio dimensional (%) AATCC 135-2004 / IN504-15	Lenght / Longitud Trans / Transversal	8% 8%
Spirality after laundry / Viraje despues del lavado (%) ISO16322-2-2005	Lenght / Longitud	5%	
	Trans / Transversal	5%	
Color fastness to wash / Solidez al lavado (gray scale) AATCC 61-2007	Change / Cambio	3.0-4.0	
	Stain / Transf	3.0-4.0	
Dye transfer to storage. Option II (gray scale) / Transferencia del color por almacenamiento. Opcion II AATCC 163-2007	Stain / Transf	3.0-4.0	
Color fastness to light (gray scale) / Solidez a la luz BS 1006-1990	Change / Cambio	3	
Color fastness to crocking (gray scale) / Solidez al frote AATCC 8-2007	Dry / Seco	3.0-4.0	
	Wet / Húmedo	3	
Color Fastness to perspiration (gray scale) / Solidez a la transpiración AATCC 15-2007	Change / Cambio	3.0-4.0	
	Stain / Transf	3.0-4.0	
Pilling / Pilling (Photographic) NTC 2051-2 / 2003			3
Type of fabric / Tipo de tejido			Knit

**Recommendations:**

